

# **Report of the classification of the reaction to fire performance**

**No. 230008744-6**

**issued 29 November 2012**

**English version**

## **Sponsor**

BASF SE  
Carl-Bosch-Str. 38

67056 Ludwigshafen  
DEUTSCHLAND

## **Order**

Classification of the reaction to fire behaviour according to DIN EN 13501-1

## **Date of order:**

9 October 2012

## **Name of the classified building product**

Flexible foam boards „Basotect G+“ in thicknesses more than 20 mm to max. 80 mm

This report determines the classification of the above-mentioned building product in accordance with the procedure given in DIN EN 13501-1 „Fire classification of construction products and building elements – part 1: classification using data from reaction to fire tests; German version EN 13501-1: 2007+A1:2009“, edition January 2010.

Publishing and copying of classification reports without permission of MPA NRW is only allowed without any changes of the content and the form of the reports.

A shortened reproduction of a certification report needs the permission of MPA NRW.

This classification report consists of 4 pages.

## 1. Description of the building product

Flexible foam boards named „Basotect G+“.

Thickness: > 20 mm to 80 mm

Density: approx. 9.0 kg/m<sup>3</sup>

Colour: light grey

## 2. Test reports and test results which form the basis of the classification

### 2.1 Test reports

Name of the laboratory	Sponsor	Number of the test report	Test method
MPA NRW	BASF SE Carl-Bosch-Str. 38 67056 Ludwigshafen GERMANY	230008744-2 of 29 Nov.2012	DIN EN 13823
MPA NRW	BASF SE Carl-Bosch-Str. 38 67056 Ludwigshafen GERMANY	230008744-4 of 29 Nov.2012	DIN EN ISO 11925-2

## 2.2 Test results

Test method	Number of tests	Parameter	Test results	
			Continuous parameter average values	Discrete parameter
DIN EN 13823	8	FIGRA <sub>0,4</sub> (W/s)	203.7	--
		THR <sub>600s</sub> (MJ)	3.1	--
		LFS < outer edge	--	yes
		SMOGRA (m <sup>2</sup> /s)	62.0	--
		TSP <sub>600s</sub> (m <sup>2</sup> )	158.7	--
		Burning droplets / particles (s)	0	--

Test method	Number of tests	Parameter	Test results	
			Continuous parameter average values	Discrete parameter
DIN EN ISO 11925-2	18 x K and 18 x F	F <sub>s</sub> ≤ 150 mm Burning droplets / particles	--	yes
			--	no

Remark: K = tested with flames exposed to the edge, F = tested with flames exposed to the surface

## 3. Classification and direct field of application

### 3.1 Reference

The classification was carried out in accordance with the clauses 11. and 14.1 of the standard DIN EN 13501-1:2010.

### 3.2 Classification

The tested material in relation to its fire behaviour is classified as: **C**

The additional classification regarding the smoke production is: **s2**

The additional classification regarding burning droplets / particles is: **d0**

This results in a classification of the reaction to fire behaviour of the tested material:

Fire behaviour	Smoke production	Burning droplets / particles
<b>C</b>	<b>s2</b>	<b>d0</b>

i.e. **C – s2, d0**

### 3.3 Field of application of the product

The classification is solely valid for the product described in clause 1 for the following fields of application:

- Directly laid and mechanically fixed onto substrates classified as A1 and A2-s1,d0 with a density of at least  $653 \text{ kg/m}^3$  and a thickness of at least 9 mm.

### 4. Restrictions

This classification report does not replace any type approval or certification of the product.

This classification report written in English language is issued additionally to the report written in German language with the same report number. In case of doubt the German version is valid solely. This classification report is only valid in combination with the German version of the report.

Erwitte, 29 November 2012



Dipl.-Ing. Rademacher  
Head of the testing body



Date of issue of this English version: 17 December 2012